



TECHNICAL DATA SHEET

ULTRA-GUARD 5700

Single Component

HIGH SOLIDS ELASTOMERIC SILICONE

DESCRIPTION

ULTRA-GUARD 5700 is a single-component silicone elastomer specifically designed to protect construction surfaces from the effects of weather and moisture. The outstanding features of ULTRA-GUARD 5700 are its high solids content, rapid cure and superior physical properties. ULTRA-GUARD 5700 is designed as a two-coat system consisting of a basecoat with a contrasting-colored topcoat.

USES

ULTRA-GUARD 5700 is designed to provide a durable elastomeric protective coating for sprayed polyurethane foam insulation. ULTRA-GUARD 5700 can be used by itself as the complete protective coating membrane. With the addition of ceramic roofing granules embedded into the coating surface, superior abrasion resistance is achieved.

ADVANTAGES

ULTRA-GUARD 5700's dry time may be shortened with the addition of an accelerator package. ULTRA-GUARD 5700 exhibits excellent adhesion to sprayed-in-place polyurethane foam as well as other construction surfaces. ULTRA-GUARD 5700 retains its flexibility and membrane integrity from -80° F to +250° F.

WEATHERING AND RESISTANCE PROPERTIES

ULTRA-GUARD 5700 has excellent appearance and good flexibility with no checking, cracking or significant discoloration after 5,000 hours Accelerated Weathering exposure in an Atlas carbon arc weatherometer according to ASTM D-822. ULTRA-GUARD 5700 has excellent heat resistance to 250° F, good salt, acid and solvent resistance, and fair alkali resistance.

ADHESION

ULTRA-GUARD 5700 adheres well to most properly prepared construction surfaces, including spray-applied polyurethane or isocyanurate foam insulation. ULTRA-GUARD 5700 can be re-coated when cured enough to allow light foot traffic or as much as 7 to 10 days between coats.

APPLICATION

ULTRA-GUARD 5700 is designed to be applied through high-pressure airless spray equipment. ULTRA-GUARD 5700's theoretical dry film thickness is 15 mils when applied at 1 gal. per 100 square feet. The minimum recommended thickness when used as a protective membrane over polyurethane foam is 35 dry mils. ULTRA-GUARD 5700 should only be applied by professional applicators. Consult **Master Pack** for specific application requirements and end uses.

APPLICATION EQUIPMENT

ULTRA-GUARD 5700 may be sprayed, brushed, or rolled. A high-pressure airless paint pump capable of producing a minimum of 4500 psi at the spray gun should be used. The pump should have a minimum of 3 gallons per minute output and be fed by a 5:1 transfer pump. Always use components rated for pump pressure. Hoses should have a maximum length of 200 feet; a minimum inside diameter of 1/2", a 3/8" whip may be used at the spray gun. The spray gun should be high pressure (5000 psi) with reverse-a-clean spray tip, having a minimum orifice of .019.

Nominal Properties

PHYSICAL PROPERTY	TEST METHOD	VALUE
*Dry Time	75 F, 50% RH	>3
*Dry Time w/Accelerator Pkg.	75 F, 50% RH	<2
Weathering QUV 5,000 hours	ASTM D-822	No degradation
Elongation	ASTM D-412	250%
Adhesion to SPF	ASTM C-794	2.3 pli
Tensile Strength (Die C)	ASTM D-412	300 psi
Durometer hardness: Shore A	ASTM D-2240	45-55
Permeability (U.S. perms)	ASTM E-96	7.9
Tear Strength	ASTM D-624	45 lbs/in
LIQUID PROPERTY	TEST METHOD	VALUE
Solids by Volume	ASTM D-2697	94% (+/- 2)
Solids by Weight	ASTM D-2697	94% (+/- 2)
Flash Point	ASTM D-56	142 F

This information is intended only as a guide for design purposes. The values shown are the average values obtained from sprayed laboratory samples. The test methods were performed per the ASTM Book of Standards. Higher or lower temperature & humidity conditions will effect dry time. The information contained herein is for purposes of identifying the product and does not constitute a warranty that the product will conform to that description. Product specifications and performance will vary depending on application methodologies, raw materials and other factors.

Safety, Health & Toxicity Data

A Material Safety Data Sheet has been prepared on this coating. All personnel who will come in contact with the product should read and understand this MSDS.

PROTECTIVE EQUIPMENT

Since the coatings are atomized into a very fine particle distribution during spray application, it is essential that maximum effort is made to protect the spray mechanic and others near the workplace from undue exposure.

VAPOR INHALATION

The best form of protection against organic solvents or potentially sensitizing vapors in the workplace is a fresh air supply. Numerous manufacturers, including the 3M Company and MSA, make full face fresh air masks. For maximum protection, we recommend use of NIOSH/MSHA approved self-contained breathing apparatus with a full-face piece operated in a positive pressure mode. In well-ventilated application conditions, the use of Type C organic vapor cartridge respirators is acceptable.

SKIN CONTACT

To prevent excessive skin contact with the sprayed product, we recommend use of fabric coveralls and neoprene or other resistant gloves.

EYECONTACT

Wear a full-face mask or OSHA-approved protective goggles.

FLAMMABILITY

Flash point is 142° F. Avoid open flame or spark sources. Avoid excessive heat. Vapors are heavier than air and may travel along the ground or may be moved by ventilation and ignited by pilot lights, other flames, sparks, heaters, smoking, electric motors or other ignition sources at locations distant from the material-handling point. Never use a welding or cutting torch on or near the drum. In case of fire, use CO₂, steam, dry chemicals or water fog.

SHELF LIFE

ULTRA-GUARD 5700 has a minimum shelf life of 6 months from the date of manufacture when stored in original unopened containers at temperature ranges between 32°F and 100°F.

The information herein is believed to be reliable, but unknown risks may be present. Master Pack warrants only that the material shall be of merchantable quality; this warranty is in lieu of all other written or unwritten, expressed or implied warranties; and Master Pack expressly disclaims any warranty for a particular purpose or freedom from patent infringement. Accordingly, Buyer assumes all risks what so ever as to the use of these materials and Buyer's exclusive remedy as to any breach of warranty or negligence claim shall be limited to the purchase price of the materials. Failure to strictly adhere to recommended procedures shall relieve Master Pack of all liability with respect to the materials or the use thereof.

The information contained herein is for purposes of identifying the product and does not constitute a warranty that the product will conform to that description.

Product specifications and performance will vary depending on application methodologies, raw materials and other factors.



PROTECTION OF THE WORKPLACE

Overspray of the coatings can carry considerable distances and attention should be given to the following:

1. Post warning signs a minimum of 100 feet from the work area.
2. Cover all intake vents near the work area.
3. Minimize or exclude all personnel not directly involved with the spray application.
4. No welding, smoking or open flames.
5. Have CO₂ or other dry chemical fire extinguisher available at the jobsite.
6. Provide adequate ventilation.

FIRST AID CONSIDERATION

Vapor inhalation problems are characterized by coughing, shortening of breath and tightness in the chest. Anyone exhibiting these types of symptoms should be immediately removed from the workplace and administered oxygen or fresh air. If the condition is prolonged or extreme, **SUMMON EMERGENCY TRAINED MEDICAL ATTENTION IMMEDIATELY.**

Effects of overexposure to vapor are characterized by nasal and respiratory irritation, dizziness, nausea, headache, fatigue, possible unconsciousness or even asphyxiation.

If ingested and the victim is conscious, give large amounts of water or milk to drink. Obtain medical attention immediately. Skin contact with liquid components can result in a rash or other irritation. Wash the affected skin area with water. Wipe residual liquid from the skin with a clean cloth, then wipe the affected area with 30% solution of rubbing alcohol. Follow the alcohol wipe with repeated washings with soap and water. If a rash or other irritation develops, see a physician.

Eye Contact with liquid or sprayed components can result in corneal burns or abrasions. Upon exposure, eyes should be flushed with water for an extensive period. **SUMMON EMERGENCY TRAINED MEDICAL ATTENTION IMMEDIATELY.**