## TECHNICAL DATA SHEET AQUA CLEAR - COMP A EPOXY CURING AGENT

Aqua Clear Comp A is a polyether triamine with low color, low viscosity and moderate reactivity in epoxy curing. The polyether backbone gives cured resins with relatively high elongation and good toughness and thermal shock resistance. It can be blended with higher viscosity curing agents to reduce viscosity or with cycloaliphatics to improve the elongation of hight  $T_9$  cured resins.

| Typical Physical                 |       | Epoxy Formulation                   |          |
|----------------------------------|-------|-------------------------------------|----------|
| Properties                       |       | Properties                          |          |
| Brookfield viscosity, cps (77 F) | 70    | Viscosity, cps (25 C)               | 1600     |
| Specific gravity, 20/20 C        | 0.981 | Pot life (min) (time to 10,000 cps) | ~300     |
| Density, lb/gal, 20 C            | 8.2   | Peak exotherm T, C (F)              | 38 (100) |
| Flash point, PMCC, F             | 196   | Time to peak T, min                 | 450      |
| Water, wt%                       | 0.1   | $T_9 C$ (F)                         | 92 (205) |
| Total acetylatables, Meq/g       | 6.8   | Tensile strength, psi               | 9500     |
| Total amine, meq/g               | 6.4   | Elongation, %                       | 9        |
| Primary amine, meq/g             | 6.1   | Flexural Strength, psi              | 15500    |
| Amine hydrogen eq. wt.           | 79    | Flexural modulus, psi               | 437000   |

The resin was a liquid DGEBA resin of approximately 12,000 cps and 188 eew; test panels were cured for 2 hrs @ 80 C (175 F) and 3 hrs @ 125 C (257 F); the Tg was determined by DSC.

Aqua Clear comp A should be mixed thoroughly with the resin. Curing at elevated temperature is desirable to develop the full properties show above. Good properties can be obtained, however, with cures at lower temperatures.

Master Pack warrants only that its products meet the stated specifications. Typical properties, where stated, are to be considered as representative of current production and should not be treated as specifications. While all the information presented in this document is believed to be reliable and to represent the best available data on these products. NO GUARANTEE, WARRANTY, OR REPRESENTATION IS MADE, INTENDED, OR IMPLIED AS TO THE CORRECTNESS OR SUFFICIENCY OF ANY INFORMATION, OR AS TO THE SUITABILITY OF ANY CHEMICAL COMPOUNDS FOR ANY PARTICULAR USE, OR THAT ANY CHEMICAL COMPOUNDS OR USE THEREOF ARE NOT SUBJECT TO A CLAIM BY A THIRD PARTY FOR INFRINGEMENT OF ANY PATENT OR OTHER INTELLECTUAL PROPERTY RIGHT. EACH USER SHOULD CONDUCT A SUFFICIENT INVESTIGATION TO ESTABLISH THE SUITABILITY OF ANY PRODUCT FOR ITS INTENDED USE. Products may be toxic and require special precautions in handling. For all products listed, user should obtain detailed information on toxicity, together with proper shipping, handling and storage procedures, and comply with all applicable safety and environmental standards.



32302 Camino Capistrano #201, San Juan Capistrano, CA – (949) 487-2068 – Fax (949) 487-2312 sales@masterpkg.com – www.MASTERPKG.com