

# **TECHNICAL DATA SHEET**

## HANDIFOAM® HFO FR LOW PRESSURE REFILL SYSTEMS

## LOW PRESSURE POLYURETHANE FOAM INFORMATION

Description	Low pressure, medium density, two-component spray polyurethane foam				
SPF	Spray Polyurethane Foam				
Applications	Designed to fill and seal various size voids, deaden sound or reduce vibration. Conforms to the requirements of ASTM E84 as a Class 1 (A) system.				
Preparation for use	Substrate must be clean, dry, firm, free of loose particles, and free of dust, grease and mold release agents. Protect surfaces not to be foamed. Read SDS, Operating Instructions, and Product Stewardship Guidelines. For additional information go to <a href="https://www.icpadhesives.com">www.icpadhesives.com</a>				
Use	Condition chemical to 75-85°F (24-29°C). Follow instructions for set-up found in the operating instructions.				
PPE					
	Recommend using in a well-ventilated area with certified respiratory protection or a powered air purifying respirator (PAPR). Wear protective glasses with side shields or goggles, nitrile gloves, and clothing that protects against dermal exposure. Read all instructions and SDS (Section 8) prior to use of any product.				
Note	FOR PROFESSIONAL USE ONLY. Always check the local building code before use. Cured low pressure polyurethane foam is non-toxic and inert.				
Temperature	Please see chart located on page 2				
<b>Product Storage</b>	Store in a dry area. Do not expose the kits or tanks to open flame or temperatures above 90°F (32°C). Excessive heat can cause premature aging of components resulting in a shorter shelf-life.				
Disposal	Refer to SDS (Section 13) for instructions. Always dispose of empty cylinders according to applicable federal, state, provincial and local regulations.				
Shelf-life	6 months				
Compatibility	Cured low pressure polyurethane foam is chemically inert and non-reactive in approved applications, and will not harm electrical wire insulations, extruded polystyrene foams, Romex <sup>®</sup> , rubber, PVC, polyethylene (i.e. PEX) or other plastics. The product is not resistant to UV rays; if left exposed the product should be coated or painted.				

TECHNICAL DATA	STANDARD	RESULTS		
<b>Density</b> Free Rise	ASTM D1622	1.75 lbs/ft³ (28.0 kg/m³)		
<b>Density</b> In-place	ASTM D1022	1.90 lbs/ft³ (30.4 kg/m³)		
Tack-Free/Expansion Time		15-30 seconds		
Cuttable		10 minutes (estimate)		
<b>K-factor-</b> Initial Initial	ASTM C518	0.143 BTU·inch/ft²·h·°F at 1" thickness 0.074 BTU·inch/ft²·h·°F at 2" thickness		
Aged 180 days @ 75°F (24°C) Aged 180 days @ 75°F (24°C)	ASTM CS16	0.155 BTU-inch/ft <sup>2</sup> ·h·°F at 1" thickness 0.081 BTU-inch/ft <sup>2</sup> ·h·°F at 2" thickness		
R-Value- Initial Initial Aged 180 days @ 75°F (24°C)	ASTM C518	7.02 at 1" thickness 13.54 at 2" thickness 6.44 at 1" thickness		
Aged 180 days @ 75°F (24°C)  Air Barrier Properties  @1.57 psf (75 Pa)	ASTM E283 - modified	12.30 at 2" thickness <0.003 cfm/ft² (<0.0152 L/s/m²)		
Perm Rating- Method A 1" Thick (2.54 cm)	ASTM E96 (Method A)	1.54 perms - Class II Vapor Retarder		
Closed-Cell Content	ASTM D2856	> 90%		
Fungi Resistance	ASTM G21	No growth		
TD053 ICP Building Solutions Group Rev 11/2022-5 Page				

TECHNICAL DATA (Continued)	STANDARD	RESULTS	
Compressive Strongth	ASTM D1621	15 lbf/in² (103 kPa) Parallel	
Compressive Strength	A31M D1021	9 lbf/in² (62 kPa) Perpendicular	
Tensile Strength	ASTM D1623	18 lbf/in² (124 kPa) Parallel	
<b>Dimensional Stability</b> -4°F (-20°C) / 30 days 158°F (70°C) & 97% R.H. / 30 days	ASTM D2126 (% volumetric change)	+ 0.01% + 10.3%	
Water Absorption	ASTM D2842	3.73%	
VOC Content	EPA Method 24 (Calculated)	culated) <25 g/L	
<b>Fire Rating-</b> Tested at 2" Thickness. <b>Class A</b>	ASTM E84	Flame Spread Index 10 Smoke Developed 350	
Fire Rating- Tested at 4" Beads	CAN/ULC-S102	Flame Spread Index 15 Smoke Developed 75	

## APPROVALS/STANDARDS/CLASSIFICATIONSAPPROVALS/STANDARDS/CLASSIFICATIONS

**ULe GREENGUARD** Gold Certification

**CCMC** Testing in progress for CAN/ULC S711.01



#### **TEMPERATURE GUIDELINES**

<b>Chemical Storage Temperature</b>	Optimum 75-85°F (24-29°C) but not <60°F (16°C) or >90°F (32°C)
Outside Application Temperature	40-100°F (4-38°C)
<b>Process Core Chemical Temperature</b>	75-85°F (24-29°C)
Surface Temperature (Substrate)	40-100°F (4-38°C)
Cured Foam	-200 to +240°F (-129 to +116°C)

## YIELD<sup>1</sup> (1.75 lbs/ft<sup>3</sup> Free Rise Density)

### Weight<sup>2</sup>

	(Per cylinder)	<b>Board Feet</b>	<b>Cubic Feet</b>	Linear Feet	Linear Feet
<b>P23220</b> System 8	97.0 lbs	1,015	84.6	15,506 ft at 1" bead	3,876 ft at 2" bead
	(44.0 kg)	(94.3 m <sup>2</sup> )	(2.39 m <sup>3</sup> )		
<b>P23093</b> System 17	201 lbs	2,002	167	30,592 ft at 1" bead	7,648 ft at 2" bead
	(91.2 kg)	(186 m <sup>2</sup> )	(4.72 m <sup>3</sup> )		
<b>P23293</b> System 27	350 lbs	3,381	282	51,651 ft at 1" bead	12,913 ft at 2" bead
	(159 kg)	(314 m <sup>2</sup> )	(7.98 m <sup>3</sup> )		
<b>P23487</b> System 60	705 lbs	7,783	649	118,913 ft at 1" bead	29,728 ft at 2" bead
	(320 kg)	(723 m <sup>2</sup> )	(18.4 m <sup>3</sup> )		
<b>P23887</b> System 120	1278 lbs	13,989	1166	213,728 ft at 1" bead	53,432 ft at 2" bead
	(580 kg)	(1,300 m <sup>2</sup> )	(33.0 m <sup>3</sup> )		

<sup>&</sup>lt;sup>1</sup> Yield is based on free-rise density. We state our core density/free-rise density when describing the foam. Applying foam into a cavity may result in higher in-place densities due to packing effects. These higher densities may result in lower yields.

<sup>&</sup>lt;sup>2</sup> Average Gross Weight

Always read all operating, application and safety instructions before using any products. Use in conformance with all local, state and federal regulations and safety requirements. Failure to strictly adhere to any recommended procedures and reasonable safety precautions shall release ICP Building Solutions Group of all liability with respect to the materials or the use thereof. For additional information and location of your nearest distributor, call ICP Building Solutions Group 1 330.753.4585 or 1 800.321.5585.

**NOTE:** Physical properties shown are typical and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions and may vary upon use, temperature and ambient conditions. Right to change physical properties as a result of technical progress is reserved. Yields shown are optimum and will vary slightly depending on ambient conditions and application. This information supersedes all previously published data. The Customer is responsible for deciding whether products and associated TDS information are appropriate for customer's use.

#### WARNING:

ICP low pressure one-component polyurethane foam sealants and adhesives (OCF), low pressure spray polyurethane foams and foam adhesives (SPF), and low pressure pour-in-place polyurethane foams (PIP) are composed of diisocyanate, hydrofluorocarbon, hydrocarbon or hydrofluoroclefin blowing agent, and a polyol blend. The urethane foam produced from these ingredients will support combustion and may present a fire hazard if exposed to a fire or excessive heat about 240°F (116°C). Read all instructions, ICP Product Stewardship Guidelines and SDS (Section 8) prior to use of any product. ICP polyurethane products are for professional use only.

Before using any OCF, SPF or PIP product, read the SDS and instructions carefully before use (<a href="www.icpadhesives.com">www.icpadhesives.com</a>). OCF Products: wear protective glasses with side shields or goggles, nitrile gloves, and clothing that protects against dermal exposure. Recommend using in a well-ventilated area. Avoid breathing vapors. SPF/PIP Products: wear protective glasses with side shields or goggles unless using a full-face respirator, nitrile gloves, and clothing that protects against dermal exposure. Recommend dispensing product in a well-ventilated area and with certified respiratory protection or a powered air purifying respirator (PAPR); however, well ventilated exterior applications may not need respiratory protection. It is the responsibility of the employer to complete a PPE evaluation and/or exposure assessment to determine if respiratory protection is required. Personal Protective Equipment can be purchased through ICP Building Solutions Group by ordering the Polyset® Contractor Safety Kit (F65251). The Contractor Safety Kit includes: nitrile gloves, contractor safety glasses, and a size Medium NIOSH-approved negative pressure half mask respirator.

Refer to each product's TDS for specifications, testing results, and other attributes. The customer is ultimately responsible for deciding whether products and associated TDS information are appropriate for customer's use. For professional use only. Building practices unrelated to materials can lead to potential mold issues. Material suppliers cannot provide assurance that mold will not develop in any specific system. Product uses a non-flammable compressed gas. Keep away from heat. Smoking and open flames, including hot work, should be prohibited in the vicinity of a foaming operation. Avoid contact with skin and eyes. May cause sensitization by inhalation and/or direct skin contact. Persons previously sensitized to Isocyanates may develop a cross-sensitization reaction to other isocyanates. Avoid prolonged or repeated breathing of vapor. Use in conformance with all local, state and federal regulations and safety requirements. Failure to strictly adhere to any recommended procedures and reasonable safety precautions shall release ICP Building Solutions Group. of all liability with respect to the materials or the use thereof. For additional information and location of your nearest distributor, call ICP Building Solutions Group 330.753.4585.

LIMITED WARRANTY and LIMITATION OF DAMAGES: ICP Building Solutions Group warrants only that the product shall meet ICP Building Solutions Group's specifications for the product when shipped by ICP Building Solutions Group. NO OTHER EXPRESSED OR IMPLIED WARRANTIES APPLY AND ANY IMPLIED WARRANTIES OF MERCHANTABILITY, NON-INFRINGEMENT OUTSIDE THE U.S. AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY DISCLAIMED. Buyer and users assume all risks of use, handling and storage of the product. Failure to strictly adhere to any recommended procedures shall release ICP Building Solutions Group from all liability. The user of the product is responsible to determine suitability of the product for the particular use. The exclusive remedy as to any breach of warranty, negligence or other claim is limited to the replacement of the product. Liability for any indirect, incidental or consequential damage or loss is specifically excluded.

#### **Cylinder Warranty Statement**

ICP Building Solutions Group warrants that the cylinder is fit to dispense ICP Building Solutions Group foam products that are loaded into the cylinder by ICP Building Solutions Group. The sole remedy for any breach of warranty is replacement of the cylinder. NO OTHER EXPRESSED OR IMPLIED WARRANTIES APPLY AND ANY IMPLIED WARRANTIES OF MECHANTABILITY, NON-INFRINGEMENT OUTSIDE THE U.S. AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY DISCLAIMED. The terms, conditions and warranties applicable to ICP Building Solutions Group's products dispensed from the cylinder are covered in other ICP Building Solutions Group documentation relating to that purchase. Liability for any indirect, incidental or consequential damage or loss specifically excluded. Buyer must not make any changes to the cylinder or the cylinder components, including plumbing. Any such change may produce dangerous results and cause damage or injury, including a loss of product stored in the cylinder. ICP Building Solutions Group is not responsible for damages or injuries resulting from any such changes. Those damages or injuries are Buyer's responsibility, and ICP Building Solutions Group may charge Buyer for the costs of any resulting cylinder damage or repairs. ICP Building Solutions Group also reserves the right to restrict future sales if the Buyer does not address safety concerns such as modified or missing plumbing, pressure relief valve activated or excessive cylinder pressure.

#### **Magnum Heated Hose Warranty Statement**

See the hose manufacturer's warranty regarding any warranty applicable to the hose. ICP Building Solutions Group makes no warranty regarding the hose and it is sold "AS IS" and ALL EXPRESSED AND IMPLED WARRANTIES ARE EXPRESSLY DISCLAIMED. Liability for any indirect, incidental or consequential damage or loss is specifically excluded.

MADE IN USA WITH GLOBALLY SOURCED MATERIALS